

PROPERTIES	TYPICAL RESULTS	TEST PROCEDURE	REMARKS
Specific Gravity	2.41	ASTM D792-08	
Water Absorption	0.03%	ASTM C373-06	
Coefficient of Linear Thermal Expansion	1.35 x 10 ⁻⁵ /°C	ASTM D696-03	
Flexural Strength	53.6 Mpa	ASTM D790-07	
Flexural Modulus	11.9 Gpa	ASTM D790-07	
Boiling Water Resistance	No effect	NEMA LD3 2000 3.5	
High Temperature	No effect	NEMA LD3 2000 3.6	
Moh's Hardness	7	MOHS Hardness Scale	
Slip Resistance - Coefficient of Friction (Received: Dry/Wet)	0.91 / 0.49 0.45 / 0.57 1.03 / 0.49	ASTM C1028-07	Neolite Leather Rubber
Slip Resistance - Coefficient of Friction (Renovated: Dry/Wet)	0.89 / 0.48 0.40 / 0.58 0.92 / 0.50	ASTM C1028-07	Neolite Leather Rubber
Compressive Strength	DRY: 213.74 Mpa WET: 251.16 Mpa	ASTM C170-09	
Stain Resistance	Passes	ANSI Z124.6-07	
Cigarette Test	Passes	ANSI Z124.6-07	
Chemical Resistance	Passes	ANSI Z124.6-07	
Impact Tests	Passes	ANSI Z124.6-07	
Fungal Resistance	No effect	ASTM G21-96	
Bacteria Resistance	No effect	ASTM G22-96	
Rockwell Hardness	114	ASTM D785-03	
Abrasion Resistance	606mg	ASTM D4060-07	Taber abrasion
Flammability	Class A	ASTM E84-09	

DISCLAIMER

The information contained herein is provided by Cheil Industries, Inc. and its subsidiaries and affiliates (collectively referred to as "Samsung") for information purposes only and should be used by individuals with technical experience and knowledge in the area. Samsung does not make any representation or warranties of the usefulness or expected result of the information, and does not assume any responsibility whatsoever related to the use of the information. Exclusion of the implied warranties may not apply in certain jurisdictions.